## **RAKU<sup>®</sup> TOOL**

## **WB-0801**

Board material

Polyurethane Board for Molds and Tools

© RAMPF Advanced Polymers GmbH & Co. KG

MAEI - Rev.Status: 02-2024/07/01 - GB

Page 1 / 2

Key Properties	Applications
<ul> <li>Good solvent resistance</li> <li>High heat deflection temperature with low density</li> <li>High mechanical strength with low density</li> <li>Low linear coefficient of thermal expansion</li> </ul>	<ul> <li>Foundry models for prototypes</li> <li>Jigs and fixtures for plastic parts</li> <li>Thermoforming tools</li> </ul>

**Mechanical Properties** 

		Unit	WB-0801
Color		visual	gray
Density	ISO 1183	g/cm³	ca. 0.80
Hardness	ISO 868	Shore D	65 - 70
Coefficient of thermal expansion	ISO 11359	10^-6K^-1	45 - 50
Deflection temperature, HDT	ISO 75	°C	85 - 90
Compressive strength	ISO 604	MPa	40 - 45
Flexural strength	ISO 178	MPa	35 - 40

Processing

The material should be processed at a temperature of  $20^{\circ}C - 25^{\circ}C$ .

Dimensions	
RAKU® TOOL WB-0801	1500 x 500 x 25 mm 1500 x 500 x 50 mm 1500 x 500 x 75 mm 1500 x 500 x 100 mm

## Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.





**WB-0801 Board material** Polyurethane Board for Molds and Tools



© RAMPF Advanced Polymers GmbH & Co. KG MAEI - Rev.Status: 02 - 2024/07/01 - GB Page 2 / 2

Handling precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see corresponding individual technical data sheets.

RAMPF Advanced Polymers GmbH & Co. KG Robert-Bosch-Str.8 - 10 | D-72661Grafenberg T+49.71 23.93 42-0

E advanced.polymers@rampf-group.com www.rampf-group.com Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby. The technical data sheet is not a specification, but contains only approximate values.