

High Impact / Flame Retardant

Flame Retardant polyurethane

Key Properties

- Excellent physical properties
- Flame retardant, UL94 V-0 equivalent
- Low viscosity
- High impact
- Free of mercury, MOCA or TDI

Applications

- Formulated for room temperature hand-batch or vacuum assisted casting methods.

Processing Properties

			Resin (Isocyanate)	Hardener (Polyol)
Mix ratio		pbw	100	60
		pbv	100	60
Density	ASTM D-792	g/cm ³	ca. 1.23	ca. 1.23
Viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 1,500	ca. 1,200

			Mixture
Mix viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 700
Gel time at 77°F (25°C)		min	8-14
Demold time at 150°F (66°C)		h	ca. 1

Cured / Mechanical Properties (approximate values)

Cure 1: 4 hour at 180°F + 24 hours at 77°F Cure 2: 7 days at 77°F			Cure 1	Cure 2
Aspect	visual		Amber	Amber
Density	ASTM D-792	g/cm ³	1.23	1.23
Shore hardness D	ASTM D-2240		75-85	75-85
Deflection temperature, HDT (66psi)	ASTM D-648	°F (°C)	212 (100)	150 (66)
Tensile strength	ASTM D-638	psi	8,000	8,000
Elongation at Break	ASTM D-638	%	5	5
Flexural strength	ASTM D-790	psi	11,000	11,000
Flexural modulus	ASTM D-790	psi	245,000	250,000
Notched Izod	ASTM D-256	ft.-lbf/in	1.8	1.8
Linear shrinkage	ASTM D-2566	in/in	0.001-0.005	0.001-0.005

High Impact / Flame Retardant

Flame Retardant polyurethane

Processing

The processing and material temperature should be between 68-77°F (20-25°C).

Formulated for hand-batch equipment. For best results, de-air the material prior to casting, then pressurize to 60 psi until cured. The hardener component will darken as it ages. It is recommended that dry nitrogen be used to protect the material from oxidizing and being moisture contaminated.

Agitate the hardener and resin before use to ensure that the formula is homogeneous.

Packaging

FX-8580 Quart Kit	3.2 lbs.
FX-8580 1 Gal. Kit	12.8 lbs.
FX-8580 5 Gal. Kit	64 lbs.
FX-8580 Drum Kit	720 lbs.

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures 59-86°F (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.
