

Board Material

Epoxy Board for Tools & Molds

Key Properties

- Extremely fine and smooth surface
- Excellent machinability
- Good dimensional stability
- Heat resistant up to 212°F

Applications

- Lay-up tools for low temperature tooling prepregs
- Vacuum forming molds
- Medium temperature applications

Mechanical Properties

			WB-0890
Color	visual		Dark blue
Density	ASTM D-792	lb/ft ³	ca. 56
Shore hardness D	ASTM D-2240		75 – 80
Coefficient of thermal expansion	ASTM D-3386	in/in/°F x 10 ⁻⁶	19 – 25
Deflection temperature, HDT	ASTM D-648	°F	212 – 230
Compressive strength	ASTM D-695	psi	8,700 – 10,200
Flexural strength	ASTM D-790	psi	5,800 – 7,300

Processing

The product should have a temperature of 68-77°F during processing.

Packaging

RAKU® TOOL WB-0890

59.1x19.7x [2, 3, 3.9, 5.9] in

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

Board Material

Epoxy Board for Tools & Molds

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.