RAKU® TOOL WB-0801



Board Material

Polyurethane Board for Tools and Molds

© RAMPF Advanced Polymers GmbH & Co. KG

PC - Rev.-Status: 01- 2024/08/02

Page 1 of 2

Key Properties

- Fine surface structure
- High HDT and very low CTE
- Good dimensional stability
- Good compressive and flexural strength

Applications

- Master models
- · Cubing models
- Tooling jigs and fixtures
- Vacuum forming tools

Mechanical Properties

			WB-0801
Color	visual		Gray
Density	ASTM D-792	lb/ft ³	ca. 49.9
Shore hardness D	ASTM D-2240		65 – 70
Coefficient of thermal expansion	ASTM D-3386	in/in/°F x 10 ⁻⁶	25 – 28
Deflection temperature, HDT	ASTM D-648	°F	185 – 194
Compressive strength	ASTM D-695	psi	5,800 - 6,500
Flexural strength	ASTM D-790	psi	5,100 – 5,800
Flexural modulus	ASTM D-790	psi	220,000 - 230,000

Processing

The product should have a temperature of 68-77°F during processing.

Packaging

RAKU® TOOL WB-0801

59.1x19.7x [1, 2, 3, 3.9, 5.9] in

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

RAKU® TOOL WB-0801

Board Material

Polyurethane Board for Tools and Molds



© RAMPF Advanced Polymers GmbH & Co. KG

PC - Rev.-Status: 01- 2024/08/02

Page 2 of 2

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.

RAMPF Group, Inc. 49037 Wixom Tech Drive Wixom, MI 48393 T +1 248. 295.0223 F +1 248. 295.0224 E info.us@rampf-group.com Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.