

High Impact / Polyethylene Feel

Impact resistant polyurethane

Key Properties

- Excellent physical properties after mild post cure
- Free of mercury, MOCA or TDI
- Tough polyethylene / polypropylene simulated product
- Very low mixed viscosity

Applications

- For hand-batch processing, vacuum assist casting or meter mix dispense methods

Processing Properties

			Resin (Isocyanate)	Hardener (Polyol)
Mix ratio		pbw	76	100
		pbv	67	100
Density	ASTM D-792	g/cm ³	ca. 1.21	ca. 1.07
Viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 75	ca. 1,600

			Mixture
Mix viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 500
Gel time at 77°F (25°C)		min	6-10
Demold time at 77°F (25°C)		h	2-4

Cured / Mechanical Properties (approximate values)

Cure 1: 2 hours at 150°F + 24 hours at 77°F Cure 2: 16 hours at 180°F + 7 days at 77°F			Cure 1	Cure 2
Aspect	visual		Translucent	Translucent
Density	ASTM D-792	g/cm ³	1.08	1.08
Shore hardness D	ASTM D-2240		65-75	65-75
Deflection temperature, HDT (66psi)	ASTM D-648	°F (°C)	147 (64)	151 (66)
Tensile strength	ASTM D-638	psi	4,605	4,700
Elongation at Break	ASTM D-638	%	35	30
Flexural strength	ASTM D-790	psi	3,800	4,100
Flexural modulus	ASTM D-790	psi	105,000	120,000
Notched Izod	ASTM D-256	ft·lbf/in	1.7	2.0
Linear shrinkage	ASTM D-2566	in/in	0.001-0.005	0.001-0.005

High Impact / Polyethylene Feel

Impact resistant polyurethane

Processing

The processing and material temperature should be between 68-77°F (20-25°C).

For best results, de-air material prior to casting, then pressurize to 60 psi until cured. If the mold is preheated to 150°F, the demold time will be reduced to an hour or less. This material does not have to be used in conjunction with heat. However, significant improvements in HDT are made when using the post cure methods above.

The components can freeze when stored or shipped in temperatures below 32°F. In the event your system freezes, call your RAMPF Group Inc. representative to discuss reconstitution methods.

Agitate the hardener and resin before use to ensure that the formula is homogeneous.

Packaging

TP-4055 Quart Kit	3.52 lbs.
TP-4055 1 Gal. Kit	14.08 lbs.
TP-4055 5 Gal. Kit	70.4 lbs.
TP-4055 Drum Kit	792 lbs.

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures 59-86°F (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.
