




formula for calculating speed (spindle)



validated cutting data for roughing

Turne	D _c	Zn	V _c	f _z	n	V _f	a _e	a _p	L ₁	L ₂
Туре	[mm]	[number]	[m/min]	[mm]	[rpm]	[mm/min]	[mm]	[mm]	[mm]	[mm]
torus	20,0	2	685	0,950	10.908	20.725	10,00	20,00	86,0	20,0
torus	12,0	2	425	0,925	11.279	20.867	6,00	12,00	55,0	16,0
torus	6,0	2	218	0,900	11.571	20.828	3,00	6,00	23,0	8,0

validated cutting data for finishing

formula for calculating axis feed rate

V _f	=	n	x	f _z	x	z _n
28500 [mm/min]	=	15000 [rpm]	Х	0,950 [mm]	Х	2 [number]

		<u> </u>		<u> </u>						
Type	D _c	Zn	V _c	f _z	n	V _f	a _e	a _p	L ₁	L ₂
Туре	; [mm]	[number]	[m/min]	[mm]	[rpm]	[mm/min]	[mm]	[mm]	[mm]	[mm]
ball	20,0	2	650	1,000	10.350	20.701	2,00	10,00	67,0	17,0
ball	12,0	2	390	1,000	10.350	20.701	1,20	6,00	52,0	10,5
ball	6,0	2	195	1,000	10.350	20.701	0,60	3,00	23,0	10,0

recommended cutting data for roughing

parameter	symbol	unit
radial infeed:	a _e	[mm]
axial infeed:	a _p	[mm]
number of teeth:	Zn	[number]

recommended cutting data for finishing

parameter	symbol	unit
radial infeed:	a _e	[mm]
axial infeed:	a _p	[mm]
number of teeth:	Zn	[number]

rougn		ualion
min.	ideal	max.
- x D _c	0,50 x D _c	0,80 x D _c
0,10 x D _c	1,00 x D _c	5,00 x D _c
1	1	2

uching recommendation

finishing recommendation				
min.	ideal	max.		
- x D _c	0,10 x D _c	0,80 x D _c		
- x D _c	0,50 x D _c	1,00 x D _c		
1	1	2		

parameter	symbol	unit
cutting speed:	V _c	[m/min]
feed/tooth:	f _z	[mm]

speed (spindle):	n	[rpm]
axis feed rate:	V _f	[mm/min]

cutting diameter:	D _c	[mm]
tool total length:	L ₀	[mm]
tool unclamping length:	L_1	[mm]
tool cutting length:	L ₂	[mm]

user	
specifications	
selection in the diagram	
selection in the diagram	

calculation by user
calculation by user

processing specific
processing specific
processing specific
processing specific

RAMPF Advanced Polymers GmbH & Co. KG

Robert-Bosch-Str. 8 -10 | 72661 Grafenberg | Germany T +49.7123.9342-0


Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal reationship, nor are any protected third party rights what's ever affected thereby.

E advanced.polymers@rampf-group.com

www.rampf-group.com







RAMPF Advanced Polymers GmbH & Co. KG

Robert-Bosch-Str. 8 -10 | 72661 Grafenberg | Germany T +49.7123.9342-0

E advanced.polymers@rampf-group.com

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal reationship, nor are any protected third party rights what's ever affected thereby.

www.rampf-group.com





cutting data used on the demonstrator

sequence of processing	processing strategy	a _e	a _p	offset	fz	V _c
roughing torus D6	vol. roughing following contour	3,00	6,00	0,60	0,90	218
roughing torus D12	vol. roughing following contour	6,00	12,00	1,20	0,25	425
roughing torus D20	vol. roughing following contour	10,00	20,00	2,00	0,95	685
finishing ball D6	zigzag stroke milling	0,60	3,00	0,00	1,00	195
finishing ball D12	zigzag stroke milling	1,20	6,00	0,00	1,00	390
finishing ball D20	zigzag stroke milling	2,00	10,00	0,00	1,00	650

tools used on the demonstrator

tool manufacturer	tool type	D _c	L ₀	L ₁	L ₂	z _n
hufschmied-tools.com/de/	PROTO-LINE / Torus	6,0	60,0	23,0	8,0	2
hufschmied-tools.com/de/	PROTO-LINE / Torus	12,0	100,0	55,0	16,0	2
hufschmied-tools.com/de/	PROTO-LINE / Torus	20,0	104,0	86,0	20,0	2
hufschmied-tools.com/de/	PROTO-LINE / Kugel	6,0	60,0	23,0	10,0	2
hufschmied-tools.com/de/	PROTO-LINE / Kugel	12,0	83,0	52,0	10,5	2
hufschmied-tools.com/de/	PROTO-LINE / Kugel	20,0	104,0	68,0	17,0	2





RAMPF Advanced Polymers GmbH & Co. KG

Robert-Bosch-Str. 8 -10 | 72661 Grafenberg | Germany T +49.7123.9342-0 E advanced.polymers@rampf-group.com Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal reationship, nor are any protected third party rights what's ever affected thereby.

www.rampf-group.com